

Description

Translucent special PVC film, providing homogenous uniformity when viewed through or on to the materials. The reduced surface gloss inhibits undesired reflection.

Release paper

Silicone coated paper on one side, 137 g/m², with special release characteristics which provide excellent waste-stripping properties. For white vinyl a light blue silicone coated paper is used to form a stronger contrast to lettering.

Adhesive

Solvent polyacrylate, permanent

Area of use

This film is especially designed for high quality application on light boxes and for production of internally illuminated signs made of acrylglas, glass and pretensioned banner material. Suitable for application on cutting plotters. Semi-glossy surface in white is additionally suitable for thermal transfer printing (with resin ribbons).

Technical data

Thickness* (without protective paper and adhesive)	80 micron
Dimensional stability (FINAT TM 14)	adhered to steel, no measurable shrinkage in cross direction, in length 0.2 mm max.
Temperature resistance	adhered to acrylglas, -40°C to +90°C, no variation
Resistance to cleaning agents	adhered to acrylic glass, 8h in washalcalics (0,5% household-cleaning agents) at room temperature and 65°C, no variation
Adhesive power* (FINAT TM 1, after 24h)	18 N/25 mm glass 16 N/25 mm acrylic glass
Tensile strength (DIN EN ISO 527)	
along	min. 19 MPa
across	min. 19 MPa
Elongation at break (DIN EN ISO 527)	
along	mind. 130%
across	mind. 150%
Shelf life**	2 years
Application temperature	> + 8°C
Service life by specialist application under vertical outdoor exposure (normal climate of Central Europe)	black / white: 7 years coloured: 7 years metallic: 5 years

* average ** in original packaging, at 20°C and 50% relative humidity

Attention:

Surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination which could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure respectively. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. Furthermore the application information published by ORAFOL is to be considered. The batch traceability according to ISO 9001 is possible on the basis of the roll number.

The statements in this information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications customers should independently determine the suitability of this material for their specific purpose, prior to use.

